

## **Product Data**

## TITANZEX HM5000 FOR MONOFILAMENT

**CHARACTER** HM5000 is a high density polyethylene for extrusion monofilament. HM5000 meets the U.S.

Food and Drug Administration (FDA) criteria for food contact use as specified in

21 CFR 177.1520 (c) 3.1a & 3.2a

**APPLICATIONS** Yarn, Ropes, Fishing nets.

**ADVANTAGES** Excellent processability, high stiffness, high draw down capability.

TYPICAL RESIN PROPERTIES	<u>UNIT</u>	$\underline{HM5000}^{(a)}$	ASTM METHOD (b)
Melt index	g/10 min	0.8	D 1238
Density	g/cm <sup>3</sup>	0.951	D 1505
Vicat Softening Point	$^{\circ}\mathrm{C}$	126	D 1525
TYPICAL MECHANICAL PROPERTIES			
Tensile strength at yield	kg/cm <sup>2</sup>	260	D 638
Tensile strength at break	kg/cm <sup>2</sup>	390	D 638
Elongation at break	%	> 500	D 638
Stiffness (Olsen)	kg/cm <sup>2</sup>	8000	D 747
Izod impact strength	kg·cm/cm	20	D 256
Shore hardness	D scale	62	D 2240
Stress cracking resistance (F <sub>50</sub> )	hr	30	D 1693

<sup>(</sup>a) Values shown are typical and are not to be considered as specifications.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

R01

<sup>(</sup>b) ASTM test methods are latest under the Society's current procedures.