

## Product Data Sheet

**PT. Lotte Chemical Titan Nusantara.** (Formerly known as PT TITAN Petrokimia Nusantara)  
**Head Office :** Mangkuluhur City Tower One, 32<sup>nd</sup> Floor, Jl. Jendral Gatot Subroto Kav. 1-3, Karet Semanggi, Setiabudi, Jakarta Selatan – 12930, Indonesia Phone: +62 21 27883355 Fax: +62 21 27883366/99  
**Site Location :** Jl. Raya Merak Km.116 Cilegon 42436, Banten Indonesia Phone +62 254 571333 Fax : +62 254 571290  
**Email:** [tsc@lottechem.co.id](mailto:tsc@lottechem.co.id) **Website :** [www.lottechem.co.id](http://www.lottechem.co.id)

### Titanvene™ HD5120EA-B

#### Organoleptic Closure Applications

Titanvene™ HD5120EA-B is a high density polyethylene copolymer with a narrow molecular weight distribution, which has been specially developed for packaging of non-carbonated beverages and for other applications where very high environmental stress cracking resistance (ESCR) is required. Titanvene™ HD5120EA-B has excellent organoleptic properties that do not significantly transfer taste or odour to the packaged product. Titanvene™ HD5120EA-B is characterised by excellent impact strength and creep resistance.

#### Applications

Titanvene™ HD5120EA-B is designed for bottle caps of non-carbonated beverages or other closures where very high ESCR is required.

#### Recommended Processing Conditions <sup>(1)</sup>

Titanvene™ HD5120EA-B can be easily processed on normal polyethylene injection moulding machines at temperatures in the range of 200°C to 240°C and compression moulding machines in the range of 160 °C to 180 °C.

#### Food Contact Compliance

Titanvene™ HD5120EA-B can be used in food contact applications. Please contact your nearest PT. Lotte Chemical Titan Nusantara representative for more detail of food contact compliance statements for the specific grade.

General Properties	Value <sup>(2)</sup>	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	2.5	g/10 min	ISO 1133 Condition 4
Nominal Density	0.954	g/cm <sup>3</sup>	ISO 1183 Method D
Vicat Softening Point	126	°C	ISO 306
Melting Point	131	°C	ISO 3146 Method C
Mechanical Properties <sup>(3)</sup>	Value <sup>(2)</sup>	Unit	Test Method
Tensile Stress at Yield	26	MPa	ISO/R 527 Type 2 Speed C
Elongation at Break	2000	%	ISO/R 527 Type 2 Speed C
Charpy Impact Strength	10	kJ/m <sup>2</sup>	ISO 179 Type 1 Notch A
Flexural Modulus	1300	MPa	ISO 178
Hardness (Shore D)	66		ISO 868 Type D
ESCR Condition B, F <sub>50</sub> <sup>(4)</sup>	40	Hours	ASTM D1693

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.

(2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.

(3) Measured on compression molded plaques.

(4) Environment Stress Cracking Resistance 10% Igepal : CO-630

**" World's 1<sup>st</sup> Halal Certified Resins - preserve integrity, wholesomeness & hygiene "**

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.