

# Product Data

## TITANEX HM4560UA-C FOR HDPE LARGE BLOW MOLDING

- CHARACTER** HM4560UA-C is an UV light stabilized, pelleted high molecular weight, high density polyethylene Hexene-1 resin for medium-large blow molding.
- APPLICATIONS** Intermediate bulk containers, agricultural containers, industrial chemical containers and pallets.
- ADVANTAGES** Excellent stress crack resistance, excellent resistance to most chemicals and outstanding rigidity with high impact strength and high melt strength.

<u>TYPICAL RESIN PROPERTIES</u>	<u>UNIT</u>	<u>HM4560UA-C (a)</u>	<u>ASTM METHOD (b)</u>
Melt index, I <sub>21</sub>	g/10 min.	<b>6.5</b>	D 1238
Density	g/cm <sup>3</sup>	<b>0.945</b>	D 1505
Tensile strength at yield	kg/cm <sup>2</sup>	<b>240</b>	D 638
Tensile strength at break	kg/cm <sup>2</sup>	<b>350</b>	D 638
Ultimate elongation	%	<b>&gt; 600</b>	D 638
Flexural modulus	kg/cm <sup>2</sup>	<b>11,000</b>	D 790
Heat deflection temperature at 4.6 kg/cm <sup>2</sup>	°C	<b>75</b>	D 648
Izod impact strength	kg.cm/cm	<b>65</b>	D 256
ESCR bent strip, F <sub>50</sub>	hrs	<b>&gt; 1,000</b>	D 1693 (c)
Vicat softening point	°C	<b>125</b>	D 1525

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

(c) 10% "Igepal", 1.9mm specimen, slit, 50°C, Procedure B

### Typical moulding conditions

Rear zone temperature setting, °C	: 180 – 220
Front zone temperature setting, °C	: 190 – 230
Head and die temperature setting, °C	: 190 – 230

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.