

Product Data

TITANEX MF1461 FOR GEOMEMBRANE

- CHARACTER** MF1461 is a pelleted linear low density polyethylene Hexene-1 resin for blown film extrusion.
- APPLICATIONS** Geomembrane, High strength film.
- ADVANTAGES** High melt strength, Excellent stress crack resistance, Excellent drawdown properties for high quality thin film.

| <u>TYPICAL RESIN PROPERTIES</u> | <u>UNIT</u> | <u>MF1461</u> ^(a) | <u>ASTM METHOD</u> ^(b) |
|---------------------------------------|-------------------|------------------------------|-----------------------------------|
| Melt index, I ₂ | g/10 min. | 0.1 | D 1238 |
| Melt index, I ₂₁ | g/10 min. | 14 | D 1238 |
| Density | g/cm ³ | 0.938 | D 1505 |
| Oxidative Induction Time, OIT @ 200°C | mins | > 130 | D 3895 |

TYPICAL SHEET PROPERTIES ^(c)

| | | | |
|--|--------------------|------------------|--------|
| Tensile strength at break | kg/cm ² | 310 | D 638 |
| Elongation at break | % | 700 | D 638 |
| Flexural modulus | kg/cm ² | 10400 | D 790 |
| Izod impact | kJ/m ² | 58 | D 256 |
| ESCR Condition B (10% Igepal), F ₅₀ | hrs | > 4000 | D 1693 |

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

(c) Compression molded specimen prepared in accordance with ASTM D 1928.

Shrinkage : 2 - 5% depending on the product wall thickness and molding parameters.

Processing conditions

Extrudable by conventional blown film extruder.

Melt temperature, °C : 180 - 200

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.