

Product Data Sheet

PT. Lotte Chemical Titan Nusantara. (Formerly known as PT TITAN Petrokimia Nusantara)
 Head Office : Mangkuluhur City Tower One, 32nd Floor, Jl. Jendral Gatot Subroto Kav. 1-3, Karet Semanggi,
 Setiabudi, Jakarta Selatan – 12930, Indonesia Phone: +62 21 27883355 Fax: +62 21 27883366/99
 Site Location : Jl. Raya Merak Km.116 Cilegon 42436, Banten Indonesia Phone +62 254 571333 Fax : +62 254 571290
 Email: tsc@lottechem.co.id Website : www.lottechem.co.id

Titanvene™ BPD3220

Wire and Cable Applications

Titanvene™ BPD3220 is a linear low density polyethylene designed for extrusion process especially in wire and cable insulation applications. Titanvene™ BPD3220 characterized by low gel content, easy extrusion without slip and anti-block additives content.

Applications

Titanvene™ BPD3220 is a wire and cable polyethylene grade applications for low voltage wire insulation.

Recommended Processing Conditions ⁽¹⁾

Titanvene™ BPD3220 can be easily processed on normal machines at temperatures in the range of 180°C to 210°C.

Food Contact Compliance

Titanvene™ BPD3220 can be used in food contact applications. Please contact your nearest PT. Lotte Chemical Titan Nusantara representative for more detail of food contact compliance statements for the specific grade

General Properties	Value ⁽²⁾	Unit	Test Method
Melt Flow Rate (190°C/2.16 kg)	2.6	g/10 min	ISO 1133 Condition 4
Nominal Density	0.920	g/cm ³	ISO 1183 Method D
Vicat Softening Point	103	°C	ISO 306
Melting Point	120	°C	ISO 3146 Method C
Mechanical Properties ⁽³⁾	Value ⁽²⁾	Unit	Test Method
Tensile Stress at Yield	12	MPa	ASTM D638
Elongation at Break	1300	%	ASTM D638
Electrical Properties	Value ⁽²⁾	Unit	Test Method
Dielectric Constant	2.54		ASTM D150
Dissipation Factor	< 10 ⁻⁴		ASTM D150
Volume Resistivity	10 ¹⁶	Ω.cm	ASTM D257

(1) The optimum processing conditions can be different from one machine to the others, depend on the mould and part design.

(2) The values shown are typical values obtained by averaging a number of tests. Small divergences from the quoted figures may occur.

(3) Measured on compression molded plaques.

" World's 1st Halal Certified Resins - preserve integrity, wholesomeness & hygiene "

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.